

WISCONSIN STONEGATE TUMBLED BLEND

SPECIFICATIONS

THIN VENEER FULL VENEER

	ORIGIN	WISCONSIN
	INFO	100% SPLITFACE, MACHINE CUT VENEER TUMBLED
	PATTERN	NATURAL COURSE, RANDOM ASHLAR.
	COLOR	GRAY, SILVER, DARK GRAY-BLUE, MAUVE
	AREA	37-40 SQFT / TON (FULL) 13-15 LBS/SQFT (THIN)
	HEIGHT	RANDOM 2" - 6", JUMPERS 6"-9"
	LENGTH	RANDOM 6" - 30" THIN VENEER CORNERS: 6"-13"
	WIDTH	FULL: 3"-5" (4") THIN: 3/4"- 1/2"
	DENSITY	167.1 - 175 LB/FT ³



ASTM - C170

COMPRESSIVE STRENGTH

23,530 - 30,850 PSI	PERPENDICULAR TO RIFT, WET
31,010 - 21,560 PSI	PERPENDICULAR TO RIFT, DRY
26,050 - 25,930 PSI	PARALLEL TO RIFT, WET
28,300 - 29,010 PSI	PARALLEL TO RIFT, DRY

ASTM - C97

ABSORPTION & SPECIFIC GRAVITY

.32% & .95%	WATER ABSORPTION
2.80 & 2.676	BULK SPECIFIC GRAVITY

ASTM - C99

MODULUS OF RUPTURE

1,650 PSI - 2,130 PSI	MODULUS OF RUPTURE, WET
1,800 PSI - 2,420 PSI	MODULUS OF RUPTURE, DRY