










# CHILTON ALPINE BLEND

## SPECIFICATIONS

THIN VENEER  FULL VENEER

	ORIGIN	CHILTON, WISCONSIN
	INFO	80% SPLITFACE, 20% COLORED WEATHEREDGE (STONEGATE & RUSTIC ANTIQUE)
	PATTERN	NATURAL COURSE, RANDOM ASHLAR
	COLOR	GRAY, SILVER, DARK GRAY, MAUVE, WITH GOLD & RED RUSTIC TONES
	AREA	37-40 SQFT / TON (FULL) 13-15 LBS/SQFT (THIN)
	HEIGHT	RANDOM 2" - 6", JUMPERS 6"-9"
	LENGTH	RANDOM 6" - 30" THIN VENEER CORNERS: 6"-13"
	WIDTH	FULL: 3"-5" (4") THIN: 3/4"- 1/2"
	DENSITY	167.1 LB/FT <sup>3</sup>



## ASTM - C170

## COMPRESSIVE STRENGTH

30,850 PSI	PERPENDICULAR TO RIFT, WET
21,560 PSI	PERPENDICULAR TO RIFT, DRY
25,930 PSI	PARALLEL TO RIFT, WET
29,010 PSI	PARALLEL TO RIFT, DRY

## ASTM - C97

## ABSORPTION & SPECIFIC GRAVITY

CHILTON: .95%	WATER ABSORPTION
CHILTON: 2.676	BULK SPECIFIC GRAVITY

## ASTM - C99

## MODULUS OF RUPTURE

1,650 PSI - 2,130 PSI	MODULUS OF RUPTURE, WET
1,800 PSI - 2,420 PSI	MODULUS OF RUPTURE, DRY

